

SALY OCEAN

|                                |                                  |
|--------------------------------|----------------------------------|
| FORMATO/ <i>FORMAT</i>         | 31,6X60                          |
| ESPESOR/ <i>THICKNESS (mm)</i> | 9,6                              |
| PRODUCTO/ <i>PRODUCT</i>       | REVESTIMIENTO / <i>WALL TILE</i> |
| TIPO/ <i>KIND</i>              | ESMALTADO/ <i>GLAZED</i>         |
| GRUPO/ <i>GROUP</i>            | BIII - GL                        |

NORMA APLICABLE EN 14411 ANEXO L  
APPLICABLE STANDARD ISO 13006 ANNEX L



| ENSAYOS/ <i>TESTS</i> |                                                                                       | RESULTADOS/ <i>RESULTS</i>                                          |                                        |
|-----------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------|----------------------------------------|
|                       | UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL                                  | DIMENSIONES                                                         | CUMPLE CON LA                          |
|                       | UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY                                     | DIMENSIONS                                                          | NORMA<br>COMPLIES WITH<br>THE STANDARD |
|                       | UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA                                                  | VALOR MEDIO (%)                                                     | 16%                                    |
|                       | UNE-EN ISO 10545-3 WATER ABSORPTION                                                   | AVERAGE VALUE (%)                                                   |                                        |
|                       | UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN                                           | FUERZA DE ROTURA                                                    | 600-900 N                              |
|                       | UNE-EN ISO 10545-4 MODULUS OF RUPTURE                                                 | BREAKING STRENGTH (N)                                               |                                        |
|                       |                                                                                       | RESISTENCIA A LA FLEXIÓN<br>MODULUS OF RUPTURE (N/mm <sup>2</sup> ) | 15 – 25 N/mm <sup>2</sup>              |
|                       | UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO                                      | RESULTADO                                                           | RESISTE                                |
|                       | UNE-EN ISO 10545-9 THERMAL RESISTANCE                                                 | RESULT                                                              | RESISTS                                |
|                       | UNE-EN-ISO 10545-11 RESISTENCIA AL CUARTEO                                            | RESULTADO                                                           | RESISTE                                |
|                       | UNE-EN-ISO 10545-11 CRAZING RESISTANCE                                                | RESULT                                                              | RESISTS                                |
|                       | UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA<br>UNE-EN ISO 10545-13 CHEMICAL RESISTANCE    | CLORURO AMÓNICO<br>AMMONIUM CHLORIDE 100 g/l                        | A                                      |
|                       |                                                                                       | HIPOCLORITO SÓDICO<br>SODIUM HYPOCHLORITE 20 mg/l                   | A                                      |
|                       |                                                                                       | ÁCIDO CLORHÍDRICO<br>HYDROCHLORIC ACID 3%                           | CUMPLE CON LA                          |
|                       |                                                                                       | ÁCIDO CÍTRICO<br>CITRIC ACID 100 g/l                                | NORMA                                  |
|                       |                                                                                       | HIDRÓXIDO POTÁSICO<br>POTASSIUM HYDROXYDE 30 g/l                    | COMPLIES WITH<br>THE STANDARD          |
|                       |                                                                                       | ÓXIDO VERDE EN ACEITE LIGERO<br>GREEN AGENT IN LIGHT OIL            | 5                                      |
|                       | UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS<br>UNE-EN ISO 10545-14 STAIN RESISTANCE | SOLUCIÓN ALCOHÓLICA DE YODO<br>IODINE SOLUTION IN ALCOHOL           | 5                                      |
|                       |                                                                                       | ACEITE DE OLIVA<br>OLIVE OIL                                        | 5                                      |
|                       |                                                                                       |                                                                     |                                        |

OBSERVACIONES:

VºBº LABORATORIO:

