

Matrix code: S24-FP/L1-K&B-Acet

Revision: 27/03/2020

Page 1 from 2

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 20 min
Curing speed * (23°C/50% R.H.)	Ca. 2 mm/24h
Hardness**	Ca. 10 ± 5 Shore A
Density**	Ca. 0.95 g/ml
Maximum allowed distortion	25 %
Max. tension (ISO 37)**	Ca. 1,80 N/mm ²
Elasticity modulus 100% (ISO 37)**	Ca. 0,20 N/mm ²
Elongation at break (ISO 37)**	Ca. 800 %
Temperature resistance**	-60 °C → 120 °C
Application temperature	5 °C → 35 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

The product is a high quality, elastic, 1-component sealant based on silicones.

Properties

- Very easy to apply
- UV-resistant
- Impervious to mould
- Permanently elastic after curing
- Very good adhesion on sanitary surfaces
- Typical acetic smell
- Not paintable
- Not suitable for natural stone

Applications

- Connection joints between wall and bathtubs or shower bases.
- For sealing of joints in sanitary and other moist rooms between e.g., showers, bathtubs and (tiled) walls, between walls and washbasins, between floors and toilet.
- Sanitary applications.

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all usual building substrates, no pvc, not suitable for concrete

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces should be primed. No primer needed for non-porous substrates.

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate.

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

Application method

Application method: With a manual, pneumatic or accu caulking gun.

Cleaning: Clean with solvent cleaner immediately after use

Finishing: With a soapy solution before skinning.

Repair: With the same material.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Matrix code: S24-FP/L1-K&B-Acet

Revision: 27/03/2020**Page 2 from 2****Health- and Safety Recommendations**

Take the usual labour hygiene into account.
Consult label and material safety data sheet for more information.

Remarks

- Because of the acid nature, certain metals (eg copper, lead) can be affected.
- Do not use on natural stones like marble, granite, ...(staining).
- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- A total absence of UV can cause a color change of the sealant.
- In an acid environment or in a dark room, a white sealant can slightly turn yellow. Under the influence of sunlight, it will turn back to its initial colour.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- We strongly recommend not to apply the Finishing Solution in full sunlight as it will dry very fast in these circumstances.
- Do not use on polycarbonate. Use Silirub PC instead.
- Do not use in applications where continuous water immersion is possible.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.