

G.B.MILTON SIENA

FORMATO/ <i>FORMAT</i>	31,6X60
ESPESOR/ <i>THICKNESS</i> (mm)	9,5
PRODUCTO/ <i>PRODUCT</i>	REVESTIMIENTO / <i>WALL TILE</i>
TIPO/ <i>KIND</i>	ESMALTADO/ <i>GLAZED</i>
GRUPO/ <i>GROUP</i>	BIII - GL

NORMA APLICABLE EN 14411 ANEXO L
APPLICABLE STANDARD ISO 13006 ANNEX L

ENSAYOS/ <i>TESTS</i>		RESULTADOS/ <i>RESULTS</i>	
	UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL	DIMENSIONES	CUMPLE CON LA
	UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY	DIMENSIONS	NORMA COMPLIES WITH THE STANDARD
	UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA	VALOR MEDIO (%)	16%
	UNE-EN ISO 10545-3 WATER ABSORPTION	AVERAGE VALUE (%)	
	UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN	FUERZA DE ROTURA	600-900 N
	UNE-EN ISO 10545-4 MODULUS OF RUPTURE	BREAKING STRENGTH (N)	
		RESISTENCIA A LA FLEXIÓN MODULUS OF RUPTURE (N/mm ²)	15 – 25 N/mm ²
	UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO	RESULTADO	RESISTE
	UNE-EN ISO 10545-9 THERMAL RESISTANCE	RESULT	RESISTS
	UNE-EN-ISO 10545-11 RESISTENCIA AL CUARTEO	RESULTADO	RESISTE
	UNE-EN-ISO 10545-11 CRAZING RESISTANCE	RESULT	RESISTS
	UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA UNE-EN ISO 10545-13 CHEMICAL RESISTANCE	CLORURO AMÓNICO AMMONIUM CHLORIDE 100 g/l	A
		HIPOCLORITO SÓDICO SODIUM HYPOCHLORITE 20 mg/l	A
		ÁCIDO CLORHÍDRICO HYDROCHLORIC ACID 3%	CUMPLE CON LA
		ÁCIDO CÍTRICO CITRIC ACID 100 g/l	NORMA
		HIDRÓXIDO POTÁSICO POTASSIUM HYDROXYDE 30 g/l	COMPLIES WITH THE STANDARD
		ÓXIDO VERDE EN ACEITE LIGERO GREEN AGENT IN LIGHT OIL	5
	UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS UNE-EN ISO 10545-14 STAIN RESISTANCE	SOLUCIÓN ALCOHÓLICA DE YODO IODINE SOLUTION IN ALCOHOL	5
		ACEITE DE OLIVA OLIVE OIL	5

OBSERVACIONES:

VºBº LABORATORIO:

